

Multilayer Greenhouse cover film

Type : DRIPLOCK DIFFUSED

C 662

Film usage	:	Greenhouse cover
Width	:	Up to 16 meters
Thickness	:	180 micron
Length	:	As required

		Test method	Units	Values
Tensile strength at break	MD	ASTM D-882	MPa	22.0
	TD	"	MPa	24.0
Elongation at break	MD	"	%	550
	TD	"	%	700
Tear resistance	MD	ASTM D1922	Gr./mm.	7000
	TD	"	Gr./mm.	10000
Falling dart drop impact		ASTM D-1709	Gram	900

Light transmission in PAR	%	ASTM D-1003	89
Diffused light tr. in PAR	%	"	72
Anti-Drip effect		Yes (place in accordance to instruction)	

Typical values

Revision 1 – 4/2017

Covering the world with care

